

Amendments to the Specification

Please rewrite substitute specification paragraph [0118], first rewritten in the Amendment filed March 1, 2010, as follows:

[0118] Evaluation Test

Bemcot was immersed in a weakly alkaline cleaner ~~having an alkaline liquid composition with a pH value of 9 or higher~~, [e.g., Cleaner IC-100S, (pH-12) manufactured by LION OFFICE PRODUCTS CORP.] and was then reciprocated by 30 times on each antireflective laminate prepared in Example 1 to Comparative Example 2 under a load of 1 kg. In this case, the following properties were measured and evaluated before and after the reciprocation and are shown in Table 1 (before the test) and Table 2 (after the test).